



POLYURETHANE 300 ALIPHATIC FINISH COAT WHITE PREMIUM POLYURETHANE ROOF COATING

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION:

ERSystems® Polyurethane 300 Aliphatic Finish Coat is a single component, aliphatic, moisture-cure, polyurethane coating. Polyurethane 300 Aliphatic Finish Coat was developed to provide the highest possible combination of flexibility, elongation, gloss and color retention, as well as excellent weathering and UV screening capabilities. In combination with substrate primers and Polyurethane 300 Aromatic Base Coat it produces a continuous, seamless, waterproof coating system.

TYPICAL PROPERTIES:

Property	Test Method	Typical Value
Percent Solid:	ASTM D2369	Weight Solids 76%, Weight Volume 75%
Viscosity:	Brookfield Viscometer	3500-7000 cps
Ultimate Elongation:	ASTMD412	475%
Tensile Strength:	ASTM D412	2390 psi
Moisture Vapor Transmission	ASTM D6083/D6694	0.0518 perm-in (15 mil thickness)
Weight/Gallon	Density Cup	10.1 lbs.
VOC Content	EPA Method 24	80 g/l
Low Temperature Flexibility	ASTM D6083/D6994	(1/4" Mandrel Bend @ -15°F) Passes, no loss in adhesion
Hardness	ASTM D2240	90A
Water Absorption	ASTM D471	4%
Cure Time		16-24 hours to recoat @ (75°F/23.9°C) 45% RH
Shelf Stability		6 months
Reflectivity-White		Initial 82%, 3 Year Aged Pending
Emittance-White		Initial 0.90, 3 Year Aged Pending

APPROVALS:

- CRRC Approved
- Title 24 Compliant

TYPICAL USES:

- Polyurethane 300 Aliphatic Finish Coat is applied over Polyurethane 300 Aromatic Base Coat as a UV stable Aliphatic Top Coat. It has excellent reflective and physical properties. It is a versatile, easily applied finish coating as part of our urethane membrane restoration system.
- The overall coating system is used maintain and extend the performance of Metal, Polyurethane Foam, Concrete, Aged Modified Bitumen, Single Ply's and other roofing substrates
- Polyurethane 300 Aliphatic Finish Coat has high solids consistency designed to provide a tough film Finish.

COLORS: Standard color is White.

PACKAGING:

- 5 Gal. Pail, 55 Gal. Drum



APPLICATION EQUIPMENT:

Application may be by brush or roller.

- **Brush or Roller:** Recommended for all areas. Use a 1/4 inch or 3/8-inch nap solvent resistant roller. The product can be squeegee applied and then back-rolled using a paint roller and/or spiked/teethed rollers to help break entrapped air pockets. (Do not "Dip" and roll)

GENERAL APPLICATION:

- All surfaces to be coated must be clean, dry, and free of contaminants, such as dirt, oil, grease, loose coatings or debris. Power wash blasting is typically required to remove contaminants. It is recommended the initial coat of Polyurethane 300 Aliphatic Finish Coat is back rolled to eliminate pin-holing. Allow 16 – 24 hours of cure time between coats. Polyurethane 300 Aliphatic Finish Coat can be applied at 1 gallon (3.79 liters) per 100 square feet in 1 coat.
- In planning application of Polyurethane 300 Plus Finish Coat consider environment and weather related conditions such as frost, dew, mist, condensation, humidity, and temperature. Temperature should be above 40°F (4.45°C), more than 5°F above the dew point and rising, for best application results.

Over Polyurethane Foam:

- (See Polyurethane Foam Insulation Roof Guideline - Polyurethanes) Follow the detailed instructions regarding characteristics of the Polyurethane foam required and preparation of the surface per the Guideline.
- Once the Polyurethane Foam surface is properly prepared, apply Polyurethane 300 Aromatic Base Coat at 2 gallons (7.57 liters) per 100 square feet in 2 passes. Allow to cure, and finish with Polyurethane 300 Aliphatic Finish Coat. Polyurethane 300 Aliphatic Finish Coat is applied at a rate of 1 gallon (3.79 liters) in one pass per 100 square feet to the cured Polyurethane 300 Aromatic Base Coat. Roofing granules may be embedded into a final tack coat of .5 gallon (1.89 liters) of Polyurethane 300 Aliphatic Finish Coat.

Over Concrete:

- (See Concrete Roof Guideline - Polyurethanes) Follow the detailed instructions in the Guideline regarding concrete surface preparation prior to applying Polyurethane 300 Aromatic Base Coat. Primer may be necessary.

ITW POLYMERS SEALANTS NORTH AMERICA, INC.

111 S. Nursery Road. Irving, TX 75060
Tel: 972-438-9111 Fax: 972-554-3939 www.itwsealants.com

8/23/2017

- Once the concrete surface is properly prepared, apply Polyurethane 300 Aromatic Base Coat at 2 gallons (7.57 liters) per 100 square feet in 2 passes. Allow to cure, and finish with Polyurethane 300 Aliphatic Finish Coat. Polyurethane 300 Aliphatic Finish Coat is applied at a rate of 1 gallon (3.79 liters) in one pass per 100 square feet to the cured Polyurethane 300 Aromatic Base Coat. Roofing granules may be embedded into a final tack coat of .5 gallon (1.89 liters) of Polyurethane 300 Aliphatic Finish Coat.

Over Aged Modified Bitumen and Aged BUR:

- Aged Modified Bitumen and Aged BUR Roof Restoration Guideline). Follow the detailed instruction in the Guideline regarding Aged Modified Bitumen and Aged BUR prior to applying the Polyurethane 300 Aliphatic Finish Coat.
- Once the Aged Modified Bitumen or Aged BUR surface is properly prepared, apply a minimum of 2 gallons (7.57 liters) per 100 square feet of Polyurethane 300 Aromatic Base Coat in 2 passes per 100 square feet in 2 passes. Allow to cure, and finish with Polyurethane 300 Aliphatic Finish Coat. Polyurethane 300 Aliphatic Finish Coat is applied at a rate of 1 gallon (3.79 liters) in one pass per 100 square feet to the cured Polyurethane 300 Aromatic Base Coat. Roofing granules may be embedded into a final tack coat of .5 gallon (1.89 liters) of Polyurethane 300 Aliphatic Finish Coat.

RE-COAT TIME:

- Polyurethane 300 Aliphatic Finish Coat White will typically cure sufficient to re-coat in 16 - 24 hours, at 75°F (23.9°C) and 45% R.H. Lower temperature and lower humidity will typically retard the cure rate and will require additional time to recoat. If more than 48 hours elapse before re-coating, consult ITW Polymers Sealants for proper re-coating procedures.

APPLICATION LIMITATION:

- Prior to the application of any top coat over new or freshly applied asphalt based product consult with the asphalt product manufacturer or NRCA guidelines for necessary asphalt cure times prior to coating.

TEMPERATURE CONSTRAINTS:

- Cold temperatures influence viscosity and pumping/handling characteristics of Polyurethane 300 Aliphatic Finish Coat. Heat increases and cold decreases the flow of Polyurethane 300 Aliphatic Finish Coat. When temperatures fall below 60°F, Polyurethane 300 Aliphatic Finish Coat can best be applied after storage at 70°F or higher for a minimum of 48 hours prior to usage. For ease of application, material temperature should be 60°F (15.6°C) minimum. If Polyurethane 300 Aliphatic Finish Coat is to be pumped at temperature below 60°F (15.6°C), insulated or heated hoses may be required. For additional cold weather application techniques and information, consult ITW POLYMERS SEALANTS NORTH AMERICA.
The temperature service range is -50°F (-45.6°C) to 200°F (93.3°C). The substrate temperature range for application is 40°F (4.45°C)–120°F (48.9°C).

LIMITATION:

- Polyurethane 300 Aliphatic Finish Coat cures by reacting with air moisture and atmospheric humidity. Partially used containers should not be left open and exposed to the air. Curing in the once opened container can be slowed by placing plastic wrap directly over the surface of the coating and tightly resealing the container. If a cured film has formed on the top of the product it should be carefully cut away prior to stirring the remainder of the product in the container. Stirring should be done at a slower speed so that it does not aerate the material. The surface film formation does not affect the performance of the remaining product.

CLEAN UP:

- Upon completion of the application, tools, hoses and equipment must be cleaned immediately with a suitable solvent such as xylene (xylol) solvent. If regulation does not permit use of Xylene, alternate such as acetone can be used.

CAUTION:

- Contains reacted polyurethane polymer, petroleum naphtha, and parachlorobenzotrifluoride. If swallowed, do not induce vomiting. If splashed in eyes, flush with clean water for a minimum of 15 minutes. In either case, call for physician help immediately. If splashed on skin, wash thoroughly with soap and water. Avoid breathing vapors and spray mists. Capable of producing severe dermatitis and bronchial spasms. Keep away from heat, sparks and open flames. Close container after use. Keep out of reach of children.
- The flow of material through pump and system could create static electricity. When pumping flammable materials, all equipment must be properly grounded to prevent static discharge and sparking, which could cause fire or explosions. Use only conductive or grounded air and material hoses, and be sure that your compressor and pump are properly grounded per manufacturer's recommendation.

PRIOR TO USE OF THIS MATERIAL,
READ ALL APPROPRIATE SAFETY DATA SHEETS

EXCLUSION OF WARRANTIES:

AS TO THE HEREIN DESCRIBED MATERIALS, ITW POLYMERS SEALANTS NORTH AMERICA, INC. MAKES NO WARRANTIES WHETHER EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OR MECHANABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SINCE THE USE OF THE HEREIN DESCRIBED MATERIALS INVOLVES MANY VARIABLES IN METHODS OF APPLICATION, HANDLING AND/OR USE, THE USER IN ACCEPTING AND USING THESE MATERIALS ASSUMES ALL RESPONSIBILITY FOR THE END RESULT. THE PURCHASE OF THIS ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT IS SUBJECT TO THE TERMS AND CONDITIONS OF AN "AS IS" SALE, AND IF THE PRODUCT IS PROVED TO BE DEFECTIVE, THE EXCLUSIVE REMEDY, AT ITW POLYMERS SEALANTS NORTH AMERICA, INC.'S OPTION, SHALL BE TO REPLACE THE DEFECTIVE ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT. ITW POLYMERS SEALANTS NORTH AMERICA, INC. SHALL NOT OTHERWISE BE LIABLE FOR LOSS OF DAMAGES, WHETHER DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL, REGARDLESS OF THE LEGAL THEORY ASSERTED, INCLUDING NEGLIGENCE, WARRANTY OR STRICT LIABILITY.

Complete technical information is available from:
ITW Polymers Sealants North America, Inc.